

DRYWIRED, LLC

TEST REPORT

SCOPE OF WORK

ASTM D2244 EVALUATION OF LIQUID NANOTINT 2.0

REPORT NUMBER

J0709.05-106-31 R0

TEST DATES

01/21/19 - 05/31/19

ISSUE DATE

07/02/19

RECORD RETENTION END DATE

05/31/23

PAGES


6

DOCUMENT CONTROL NUMBER

ATI 00231 (09/05/17)

RT-R-AMER-Test-2827

© 2017 INTERTEK



TEST REPORT FOR DRYWIRED, LLC

Report No.: J0709.05-106-31 R0

Date: 07/02/19

REPORT ISSUED TO

DRYWIRED, LLC

9606 S. Santa Monica Boulevard, 4th Floor
Beverly Hills, California 90210

SECTION 1

SCOPE

Product: Liquid NanoTint 2.0 by DryWired, LLC

Intertek Building & Construction (B&C) was contracted by DryWired, LLC, Beverly Hills, California, to evaluate Liquid NanoTint 2.0 in accordance with ASTM D2244. Results obtained are tested values and were secured by using the designated test methods. Testing was conducted at the Intertek B&C test facility in York, Pennsylvania.

This report does not constitute certification of this product nor an opinion or endorsement by this laboratory.

For INTERTEK B&C:

COMPLETED BY:	Jonathan Bright
TITLE:	Engineer Materials Laboratory
SIGNATURE:	
DATE:	07/02/19

REVIEWED BY:	Joseph M. Brickner
TITLE:	Laboratory Manager Materials Laboratory
SIGNATURE:	
DATE:	07/02/19

JMB:jmb/kf/als

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

TEST REPORT FOR DRYWIRED, LLC

Report No.: J0709.05-106-31 R0

Date: 07/02/19

SECTION 2

TEST METHODS

The specimens were evaluated in accordance with the following:

ASTM D2244-16, *Standard Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates*

SECTION 3

MATERIAL SOURCE

The materials were provided by DryWired, LLC and identified as Liquid NanoTint 2.0. The following was received: one 2" square specimen. The material was tested as received. Representative materials will be retained by Intertek B&C for a minimum of four years from the test completion date.

SECTION 4

LIST OF OFFICIAL OBSERVERS

NAME	COMPANY
Jonathan Bright	Intertek B&C
Joseph M. Brickner	Intertek B&C

SECTION 5

TEST PROCEDURE

All conditioning of test specimens and test conditions were at standard laboratory conditions unless otherwise reported. Refer to the test related photos in Section 9.

ASTM D2244 - Color Measurement

The color of the glass was determined utilizing a GretagMacBeth Color i5 spectrophotometer (ICN: 004725) with diffuse spherical geometry and a xenon lamp, CIElab color space, D65 illuminant, a 10° observer, and the specular component included.

SECTION 6

TEST SPECIMEN DESCRIPTIONS

TEST PROCEDURE	NUMBER OF SPECIMENS	NOMINAL SPECIMEN DIMENSIONS	VISUAL CHARACTERISTICS
ASTM D2244	1	2" square	Blue tinted coating on glass substrate

TEST REPORT FOR DRYWIRED, LLC

Report No.: J0709.05-106-31 R0

Date: 07/02/19

SECTION 7

TEST RESULTS

ASTM D2244 - Color Difference

SPECIMEN	L*	a*	b*
1	37.26	-3.16	-2.72
2	37.38	-3.16	-2.80
3	37.34	-3.18	-2.70
Average	37.33	-3.17	-2.74

SECTION 8

CONCLUSION

There were no performance requirements for ASTM D2244 Color Measurement.

TEST REPORT FOR DRYWIRED, LLC

Report No.: J0709.05-106-31 R0

Date: 07/02/19

SECTION 9 PHOTOGRAPHS



Photo No. 1
ASTM D2244 Test Setup



Total Quality. Assured.

130 Derry Court
York, Pennsylvania 17406

Telephone: 717-764-7700
Facsimile: 717-764-4129
www.intertek.com/building

TEST REPORT FOR DRYWIRED, LLC

Report No.: J0709.05-106-31 R0

Date: 07/02/19

SECTION 10

REVISION LOG

REVISION #	DATE	PAGES	REVISION
0	07/02/19	N/A	Original Report Issue