



PRECISION TESTING LABORATORIES, INC.

313 Hill Avenue, Nashville TN 37210
Phone 615-254-3401 Fax 615-254-3488
www.precisiontesting.com

Laboratory Report No. 41094 A
15-Jan-19

Page 1 of 1

Mr. Larry Eichel
DryWired, LLC
9606 S. Santa Monica Blvd
4th Floor
Beverly Hills, CA 90210

Cc: n/a

P.O. TS-TESTING-LE

Item: One (1) sample of material

Identification: Textile Shield

Purpose: Water Repellency: Spray Test; AATCC 22

Test, Unit of Measure	Specimen Results			Average
Unit of Measure				
Water Repellency: Spray Test				
AATCC 22				
	<u>Face</u>	95	<u>Class</u> 95	95
AATCC Standard Spray Test Ratings Chart used to evaluate Water Repellency test specimen				
Class 100 = No sticking or wetting of upper surface.				
Class 90 = Slight random sticking or wetting of upper surface.				
Class 80 = Wetting of upper surface at spray points.				
Class 70 = Partial wetting of whole of upper surface.				
Class 50 = Complete wetting of whole of upper surface.				
Class 0 = Complete wetting of whole of upper and lower surfaces.				

This report is limited to and related only to the particular instrument, material or other subject to which it refers. These test results can not be compared to results obtained using different methods or under different conditions. No representation is made that similar articles will be of like quality. Neither Precision Testing Laboratories, Inc (hereinafter "Precision Testing") nor their officers, directors, managers or employees, shall be responsible for any loss or damage resulting directly or indirectly from any failure, error or omission in testing, or in the reporting of test results. Precision Testing has no controls, and assumes no responsibility for the tested product's functionality or use. Precision Testing's liability shall not exceed the fees paid for the testing reflected on this report. Precision Testing observes and maintains client confidentiality, and limits reproduction of this report, except in full, without prior approval of Precision Testing. tl

Signed: Suzanne Piispanen
Suzanne Piispanen, COO